


Performance Calculator



Laminated Glass
(6+0,38+6) mm Clear 66.1

Daylight Properties (EN 410)

Daylight Transmittance	: 88%
Daylight Reflectance Outdoor	: 8%
Daylight Reflectance Indoor	: 8%

Solar Energy Properties (EN 410)

Solar Energy Direct Transmittance	: 72%
Solar Energy Reflectance Outdoor	: 7%
Solar Energy Absorption	: 21%
Solar Heat Gain Coefficient (Solar Factor / g)	: 77%
Shading Coefficient	: 0.88
UV Transmission	: 7.7%

Thermal Conductivity (EN 673)

U Value W/(m ² K)	: 5.6
------------------------------	-------

Sound Insulation Value (EN 12758)

Rw (C; Ctr) dB	: 35 (-1; -3)
----------------	---------------